



Producer: Petkim Petrokimya Holding A.S. / Turkey

PETİLEN I22-19T

Applications: Injection Moulding (kitchen goods, toys, caps and closuers), masterbatch.

PROPERTIES	UNIT	VALUE	TEST METHOD
Guaranteed values			
Melt Flow Rate (MFR)(2160 g, 190°C)	g/10 min	17-29	ASTM D-1238
Density, 23°C	g/cm ³	0.917-0.921	ASTM D-1505

Packing:

In 25 kgs Form Fill Sealed white colored PE bags loose or palletized and shrinkwrapped or in 1400 kgs big bags

Storage conditions:

In closed and dry areas, sheltered from direct sunshine.

Note:

Typical values are the average results of analyses made in Petkim Laboratories, provided for information only. This grade has certificate for production of the material in contact with foodstuffs as received by Ministry of Agriculture and Village Affairs dated 21.02.2007 and no. 35-00213-00009-0.