



Producer: Nova Chemicals / The United States (USA)

## Novapol LDPE-LF-0323-B

**Description:**

Novapol LDPE

**Application:**

Bakery bags, sandwich bags, zipper lock bags, cast film

**Additive Package:**

Slip and Antiblock

PROPERTIES	TEST METHOD	UNIT	VALUE
Melt Index <sup>(1)</sup>	D 1238	g/10 min	3.2
Density	D 792	g/cm <sup>3</sup>	0.923
Thickness		um (mil)	38 (1.5)
<b>Film properties</b>			
Dart Drop Impact	D 1709/A	g	90
Low Friction Puncture	J/mm	(in-lb-mil)	15 (3)
Tear Strength MD	D 1922	g	230
Tear Strength TD	D 1922	g	230
Tensile Strength MD	D 882	Mpa (psi)	20 (2900)
Tensile Strength TD	D 882	Mpa (psi)	18 (2600)
Yield Strength MD	D 882	Mpa (psi)	10 (1450)
Yield Strength TD	D 882	Mpa (psi)	10 (1450)
Elongation MD	D 882	%	400
Elongation TD	D 882	%	550
1% Secant Modulus MD	D 882	Mpa (psi)	165 (24000)
1% Secant Modulus TD	D 882	Mpa (psi)	180 (26000)
Haze	D 1003	%	8
Gloss @45°	D 2457		70
Coefficient of Friction	D 1894		<0.3

<sup>(1)</sup> - Condition 190/2.16