



Producer: Rompetrol Petrochemicals / Romania

LDPE Grades

GRADE	MFI (g / 10 min)	DENSITY (g/cm ³)	ADDITIVES	APPLICATIONS
<u>Extrusion solutions</u>				
LDPE B22/0.25	0,25	0,92	AOX	Blown film, shrink film
LDPE B20/0.3	0,3	0,92		Blown film, heavy duty bags
LDPE B21/0.5	0,5	0,92	S	Blown film, film for liquid packaging and co-extrusion
LDPE B22/0.7	0,7	0,92	AOX	Blown film, agriculture film
LDPE B22/1	1	0,92	AOX	Blown film, agriculture film
LDPE B20/2	2	0,92		Blown film, thin film for fine packaging with good transparency
LDPE B21/2	2	0,92	S	Blown film, thin film for fine packaging with good transparency
LDPE B20/3	3	0,92		Blown film, thin film for extra fine packaging with good transparency
LDPE B21/3	3	0,92	S	Blown film, thin film for extra fine packaging with good transparency

B – basic stabilization with antioxidants and halogen scavenger

NA - nucleating agent