



Technical Information

LLDPE NATURAL RECYCLED PELLETS

Process

Blowing, Injection, Extrusion

Physical

Density	0.920-0.925 g/cm ³
Melt Density	0.765 g/cm ³
Melt Index (190°C/2.16 kg)	2.1 to 2.3 g/10 min (ASTM D1238)
Thickness	3.08 mm
Width	4 mm
Force at break	280 N (DIN 53504)
Elongation at break	690 % (DIN 53504)
Tensile strength	22.5 MPa (DIN 53504)
Filter Used	120 mesh

Storage

This product should be stored in a dry area with an ambient temperature below 50 degrees. It should be kept away from sunlight, sparks, heat and flame.

Packaging

Our products are packed in 1200 kg big bags.

Notes

These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests. Please contact for product samples.



BURKAY & UĞUR CHEMICALS
Barakfakih Mh. 7. Cd. No:2 Kestel / Bursa
T: +90 224 384 15 31 / F: +90 224 384 13 53
info@burkay.com.tr / www.burkayugur.com.tr