

Producer: NOVA CHEMICALS / THE UNITED STATES (U.S.A)

## LDPE NOVAPOL LF-0222

**Melt Index 2.2**
**Density 0.922**
**Slip 750**
**Antiblock 1700**

### Features

- High optical clarity
- Easy processability
- Blends well with LLDPE

### Additives

- Slip
- Antiblock

### Applications

- Produce and bakery film
- General packaging requiring high clarity film

PROPERTY	TEST	UNIT	VALUE
Melt Index <sup>(3)</sup>	D 1238	2.2	g/10 min
Density	D 792	0.922	g/cm <sup>3</sup>
<b>Film Properties<sup>(4)</sup></b>			
Thickness		38	µm
Tear Strength	MD D 1922	168	g
	TD	300	g
Dart Drop Impact, F <sub>50</sub>	D 1709/A	100	g
Tensile Strength	MD D 882	21	MPa
	TD	19	MPa
Yield Strength	MD D 882	10	MPa
	TD	10	MPa
Elongation	MD D 882	420	%
	TD	570	%
Haze	D 1003	7	%
Gloss @ 45°	D 2457	73	

(1) Properties designated have been determined using methods which are in accordance with, or substantially in accordance with, the specified testing standards.

(2) Typical Values represent average laboratory values and are intended as guides only, not as specifications.

(3) Condition 190°C/2.16 kg.

(4) Film properties are typical of blown film extruded on a 1.5" extruder with 3" die and 35-mil die gap at a blow up ratio of 2.5:1, but are dependent upon operating conditions.

## Availability

NOVAPOL LF-0222-B polyethylene resins are available in bulk hopper cars, hopper trucks, boxes, sea bulk containers, or bags. The product type and batch number are clearly marked on each container. Contact the NOVA Chemicals sales office nearest you for availability in your area.

## Storage/Handling

NOVAPOL LF-0222-B resin should be stored in a clean, dry place at ambient temperatures. Prolonged or improper storage can result in deterioration of product properties. Care should be taken when handling and transferring product to prevent foreign matter contamination. The NOVA Chemicals Material Safety Data Sheet (MSDS) contains important safety information and should be reviewed before using the product.

## Processing Conditions

Comprehensive assistance with processing conditions and technology is available from NOVA Chemicals Technical Service at (403) 291-8444.

## Food Packaging Status

United States: NOVAPOL LF-0222-B resin complies with the specifications contained in the U.S. Food and Drug Administration (FDA) regulation 21 CFR 177.1520 for olefin polymers, para. (c) 2.2, and may thus be used in the United States as an article or component of an article intended for use in contact with food, without temperature or food-type restrictions, subject to technical suitability.

Other Countries: For regulatory compliance information for other countries, please contact your nearest NOVA Chemicals office.

## Environmental

NOVA Chemicals polyethylene resins are biologically and chemically inert, but improper disposal may present an ingestion hazard to wildlife. Where recycling of NOVA Chemicals' polyethylene resins is not possible, disposal to landfill or incineration in accordance with all applicable government laws and regulations is recommended. Please contact NOVA Chemicals Technical Service for further information on recycling and disposal of NOVA Chemicals resins.



is the SPI resin code developed for low density and linear low density polyethylene to identify material type for sorting and recycling purposes.