

Producer: Petkim Petrokimya Holding A.S. / Turkey

PETVINIL S39/71

Applications:

Insulation and sheathing of cables, sole of shoes, flexible and semirigid profiles and pipes, flexible films and plates, toys.

PROPERTIES	UNIT	VALUE	TEST METHOD
Guaranteed values			
Viscosity Index (In Cyclohexanone At 25°C)	cm ³ /g	121-134	SOLVAY 1A/93
K Value (In Cyclohexanone At 25°C)	-	69-72	SOLVAY 1A/93
Apparent Bulk Density	g/cm ³	0.44-0.53	SOLVAY 4A/91
Screen Analysis:			
<i>Remaining on 0.250 mm sieve</i>	% wt	Max.3	SOLVAY 8A/92, 8F/92
<i>Remaining on 0.063 mm sieve</i>	% wt	Min. 90	SOLVAY 8A/92, 8F/92
Volatiles	% wt	Max.0.5	SOLVAY 2A/90
Impurities	piece/ft ²	Max.60	SOLVAY 2A/90

Packing:

In 25 kgs Form Fill Sealed white colored PE bags , loose or palletized and shrinkwrapped or in 1400 kgs big bags

Storage conditions:

Storage in closed and dry areas is recommended.

Note:

This grade has certificate for production of material in contact with foodstuffs as received by Ministry of Agriculture and Village Affairs dated 21.02.2007 and no. 35-00214-00005-1.